

P 90/40

Technical Data

Bottom (A)
Top (B)
Height (C)
Side wall paper basis weight
Bottom paper basis weight
Mold weight
Heat resistance

GTIN-14

	Tolerance		
90 mm	± 1 mm		
93.5 mm	± 1 mm		
40 mm	± 1 mm		
95 g/m²	± 5 %		
141 g/m²	± 5 %		
2.5 g	± 5 %		
390° F max			

G9F01001



Characteristics

Side wall material Pure unbleached paper pulp, highly calendered. Single face "F" flute corrugate created from two sheets of 60 GSM pure unbleached paper, highly **Bottom Material** calendered. Smooth face creates the interior surface of the mold. Exterior surface is unprinted. Printing Gold flower design on brown background. Gold PMS 872 C, Brown PMS 504 C, resistant to heat, oil and alcohol up to recommended max Ink baking temp of 390 degrees F. Glue Vinyl acetate - water based. Used to attach side wall to base of mold. Starch Maize (corn based) used in the corrugation process. Used in the base of the mold. **FDA** Baking mold is manufactured in compliance with 21 CFR 176.170 and 176.180. Kosher Certified by KOF-K Supervision of Teaneck, New Jersey. Country of origin Italy

Additional specification documents available upon request.

Packaging and Storage

16 in x 15 in x 12.5 in Case Cube 1.736 ft³ Case weight Gross 7.5 lbs. Net 6.5 lbs. 1,200 pcs. (100 pcs. * 12 rows) Pieces/case Tie/high 6 boxes per 7 levels at 93" high 50,400 Pieces/pallet Item code, description, quantity, production Box Label number, production date, and operator. Dry conditions. Three year shelf life. Storage

18051768023625



(01)18051768023625(10)123456(15)991231(422)380

Prepared	Approved	Date	Revision	Modifications
C Bucguin Quality Manager C. Bruseghini	AND THE PROPERTY OF THE PROPER	8/17/18	7	Revision 7: General modifications.



P 90/40

Technical Data


Bottom (A)
Top (B)
Height (C)
Side wall paper basis weight
Bottom paper basis weight
Mold weight
Heat resistance

	Tolerance		
90 mm	± 1 mm		
93.5 mm	± 1 mm		
40 mm	± 1 mm		
95 g/m²	± 5 %		
141 g/m ²	± 5 %		
2.5 g	± 5 %		
390° F max			

G9F01001



Technical Drawing



Prepared	Approved	Date	Revision	Modifications
C Buseydin Quality Manager C. Bruseghini	Am.	8/17/18	7	Revision 7: General modifications.